

ECTC Classification	Installed Slope Maximum	Product Description
1C	3:1 (H:V)	Single-net Erosion Control Blankets

Rolled Erosion Control Products



Page 1 of 1

Product Name	Company Name	Material Composition	C Factor ^b <i>Performance Test</i>	Shear Stress ^c <i>Performance Test</i>	MD	TD	Material Thickness <i>Typical</i>	Ground Coverage <i>Typical</i>	Material Mass <i>Typical</i>	Installed Slope Steepness <i>Maximum</i>
					Material Tensile Strength <i>Typical</i> ASTM D6818	Material Tensile Strength <i>Typical</i> ASTM D6818				
ECTC Spec	n/a	Processed degradable natural and/or polymer fibers mechanically bound together by a single rapidly degrading, synthetic or natural fiber	≤ 0.10	≥ 1.5 lbs/ft ² (48 Pa)	≥ 60 lbs/ft (0.9 kN/m)	≥ 20 lbs/ft (0.3 kN/m)	≥ 0.25 in - ≤ 0.50 in (≥6.4 - ≤ 12.7 mm)	≥ 50 % — ≤ 90 %	≥ 8.0 oz/yd ² (271 g/m ²)	3:1 (H:V)
ECS-1D	East Coast Erosion Control	Straw	0.02	1.50 lbs/ft ²	121 lbs/ft	79 lbs/ft	0.30 in	78 %	8.0 oz/yd ²	3:1 (H:V)
S31UVD	ErosionControlBlanket.com	Straw	0.10	1.5 lbs/ft ²	132 lbs/ft ²	27.6 lbs/ft	0.25 in	78.3 %	8.0 oz/yd ²	3:1 (H:V)
AEC Premier Straw Single Net	American Excelsior Company	Straw	0.05	1.55 lbs/ft ² (74 Pa)	132. 2 lbs/ft	46.8 lbs/ft	0.31 in (7.87 mm)	78.4 %	6.88 oz/yd ²	
Curlex I CL	American Excelsior Company	Wood Fiber	0.039	1.60 lbs/ft ²	87.6 lbs/ft	30.0 lbs/ft	0.382 in	52.3 %	6.4 oz/yd ²	
Curlex I QuickMow	American Excelsior Company	Wood Fiber	0.018	1.75 lbs/ft ² (84 Pa)	78.0 lbs/ft	37.2 lbs/ft	0.411 in (10.44 mm)	79.5 %	9.12 oz/yd ²	

- C Factor and permissible shear stress for Types 1.A. and 2.A. mulch control nettings must be obtained with netting used in conjunction with pre-applied mulch material.
- This value should be the maximum C Factor from standardized large-scale rainfall performance testing, ASTM D5459 or equivalent deemed acceptable by the engineer.
- Required minimum shear stress RECP (unvegetated) can sustain without physical damage or excess erosion (> 12.7 mm (0.5 inch) soil loss) during a 30-minute flow event in large-scale performance testing, ASTM D6460 or equivalent deemed acceptable by the engineer.
- This value should represent the maximum gradient the product should be recommended for rainfall/slope application.